



Alumina Crucibles and Substrates

Epsom, Running Horse, Burrough Green, Nr Newmarket, Suffolk CB8 9NE
Tel +44 [0]1638 508712 Fax +44 [0]1638 508705
VAT Number GB 666 0691 15

Technical Data Sheet: Zirconia – CaO (5.5%) Stabilised

Description

A fully dense, fine grained zirconia stabilised with 5.5wt% CaO. This zirconia has a fully stabilised microstructure at all temperatures. It has good strength, excellent dimensional stability and is electrically conductive at higher temperatures.

Physical Data

Colour	White
Apparent Porosity	<0.1%
Density	5.37 g/cm ³
Max service temperature	>2000°C

Compositional Data

Oxide	Composition
Zirconia and Hafnia (ZrO ₂ + HfO ₂)	>93.5%
Lime (CaO)	5.5%
Magnesium Oxide (MgO)	<0.1%
Silica (SiO ₂)	<0.2%
Alumina (Al ₂ O ₃)	<0.03%
Iron oxide (Fe ₂ O ₃)	<0.1%
Titanium Oxide (TiO ₂)	<0.1%
Uranium / Thorium oxide (U ₃ O ₈ + ThO ₂)	<0.05%